

MUSEUM

CALACATTA EXTRA GOLD NT/150X320

Modell: **CALACATTA EXTRA GOLD NT/150X320**

Referenz: **32059** **GOLD**

Format: **150X320** cm

Stärke: **12,00** mm

Oberfläche: **Natural**

Art der Fliese **FEINSTEINZEUG** **Bla GRUPPE**

GL - GLASIERT

Mechanische Eigenschaften

| | | |
|-----------------|---------------------------------|------------------|
| EN ISO 10545-11 | Beständigkeit gegen Glasurrisse | Bestanden |
| EN ISO 10545-12 | Frostsicherheit | Bestanden |
| EN ISO 10545-9 | Lineare thermische Dehnung | Bestanden |

Oberflächeneigenschaften

| | | |
|----------------|-----------------------------------|--------------------------------|
| EN ISO 10545-7 | Abriebfestigkeit der Glasur (PEI) | - |
| EN ISO-10545-6 | Beständigkeit gegen tiefen Abrieb | < 175 mm³ |
| EN-101 | Oberflächenhärte (Mohs-Scala) | 6 |

Chemische Beständigkeit

| | | |
|-----------------|----------------------------------------------------------|--------------------|
| EN ISO-10545-13 | Säure- und Laugenbeständigkeit (hohe Konzentration) | ---/---/--- |
| EN ISO-10545-13 | Säure- und Laugenbeständigkeit (geringe Konzentration) | ---/LA/LA |
| EN ISO-10545-13 | Haushaltschemikalien und Badewasserzusätze Beständigkeit | A/A |
| EN ISO-10545-14 | Fleckenbeständigkeit | 5/-/5/5 |

CE-Kennzeichnung



CE-Kennzeichnung:

001CPR2017-08-01

Before laying the tiles, check the shade, calibre and quality. No claims will be accepted once the tiles have been laid. Leave a tile joint of at least 0.5 mm in the case of rectified tiles and 1.5 mm for non-rectified ones. The tile colour shown in this data sheet is merely indicative and it might differ from the real tile colour. This document is purely for sales purposes and it cannot be used in any legal or administrative proceedings, in a witness statement, or as documentary proof without the express permission of PERONDA GROUP.